



## HICKORY SPRINGS OF CALIFORNIA, INC.

### PRODUCT DATA SHEET

Code Number: 3013  
Date Issued: 12-10-99  
Supercedes: 3-4-94

TITLE: POLYESTER FLEXIBLE POLYURETHANE FOAM

ITEM	PRODUCT DATA
Density, lbs/ft. <sup>3</sup>	4.0 ±0.20
Indentation Force Deflection, 25%	60 ±5
Cell Count, cells per lineal inch	50 ±10
Tensile Strength, P.S.I. minimum	20
Elongation, % minimum	200
Tear Resistance, lbs. per inch, minimum	3.0
Compression Set, 22 hours @ 220° F., 50%, maximum	22.0
Clickability	Good
Color	Per Customer Request
<b>Flammability:</b>	
MIL-P-26514F, Type 1, Class 2, Grade C	Pass
DMS-1956F, Type 1, Class 2, Grade A	Pass
ASTM-D-1692	Pass
MVSS 302	Pass
FAA 25.853b (Vertical burn)	Pass
UL-94, HF-1	Pass

Certification to any of the above specifications shall be provided upon request.

The physical properties listed above are typical properties and are not intended as a guarantee or warranty.

NOTE: Flammability standards as listed above are based upon laboratory tests and do not describe the performance of the product in an actual fire situation. Use of flame retardants in polyurethane foam is designed to retard initial ignition and slow down initial burn rates.

4542 East Dunham Street • Los Angeles, California 90023  
(213) 266-0422 • (800) 698-1811