



ETHAFOAM* HS 900

Brand Polyethylene Foam Plank

ETHAFOAM HS 900 polyethylene foam is a strong, resilient, high-density (9.5 pcf), closed-cell foam. It has the highest strength of all current ETHAFOAM brand polyethylene foam products, and is ideally suited as a component

material in products requiring a shock absorbing, vibration dampening, insulating, barrier or buoyancy component, and as a material for cushioning components in packaging applications for impacts or loadings up to 20.0 psi.

Size available: Plank; 2" x 24" x 108"

Color available: Natural

Physical Properties [†]	Test Method	Direction	Value
Density	ASTM D 3575, Suffix W, Method B	N/A	9.5 pcf
Compression Set	ASTM D 3575, Suffix B	Vertical	<15%
Compressive Creep @ 20.0 psi (1000 hr/72°F)	ASTM D 3575, Suffix BB	Vertical	<10%
Compression Deflection @ 10%	ASTM D 3575, Suffix D	Vertical	50 psi
		Extruded	120 psi
		Horizontal	80 psi
@ 25%		Vertical	55 psi
		Extruded	125 psi
		Horizontal	85 psi
@ 50%		Vertical	90 psi
		Extruded	160 psi
		Horizontal	125 psi
Thermal Stability (linear change)	ASTM D 3575, Suffix S	N/A	<1%
Thermal Conductivity		Vertical	0.4 Btu-in/hr-ft ² -°F @ 75°F
Water Absorption	ASTM D 3575, Suffix L	N/A	<0.2 lb/sq ft
Buoyancy		N/A	52 lb/cu ft
Tensile Strength @ peak	ASTM D 3575, Suffix T	Average	180 psi
Tensile Elongation (linear change)	ASTM D 3575, Suffix T	Average	31 %
Tear Strength	ASTM D 3575, Suffix G	Average	51 lb/in

[†]The data presented for this product are for unfabricated ETHAFOAM brand polyethylene foam products. While values shown are typical of the product, they should not be construed as specification limits.

– See reverse side for additional properties and product information.

Product Features

ETHAFOAM HS 900 polyethylene foam is durable, high-strength, solid extruded plank that meets or exceeds the requirements for U.S. Federal Standard PPP-C-1752D, Type V. As the properties listed on reverse suggest, ETHAFOAM HS 900 polyethylene foam offers excellent strength, resistance to creep under load, vibration and shock absorbency and water resistance characteristics.

ETHAFOAM HS 900 polyethylene foam is produced with Dow's patented *RapidRelease* manufacturing process. This new process technology incorporates a patented CFC- and HCFC-free blowing agent system and an accelerated curing system that reduces residual blowing agents in ETHAFOAM brand polyethylene foam products to trace amounts.

ETHAFOAM HS 900 polyethylene foam meets the requirements of the U.S. Clean Air Act Amendments. It is easily fabricated, impervious to most chemicals, non-abrasive and performs consistently over a wide range of temperatures. ETHAFOAM HS 900 polyethylene foam is also reusable and completely recyclable.

Flammability

ETHAFOAM HS 900 polyethylene foam has successfully passed MVSS 302 flammability testing, conducted according to the Code of Federal Regulations, CFR 49.

For Additional Information or Technical Support

For information on products, design assistance and testing services available from Dow, call 1-800-441-4369.

CAUTION: ETHAFOAM brand polyethylene foam is combustible and should not be exposed to flame or other ignition sources.

NOTICE: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

March 1996 The Dow Chemical Company

The Dow Chemical Company, 2020 Dow Center, Midland, MI 48674
Dow Chemical Canada Inc., P.O. Box 1012, 1086 Modeland Rd., Sarnia, Ont. N7T 7K7
Dow Quimica Mexicana, S.A. de C.V., Av. Paseo de las Palmas 555-3, Lomas de Chapultepec, Mexico 11000 D.F., Mexico

